

## Product Data

# ProtoGen™ 18120

a DSM Product

Sales Agent:



RP Support Ltd.

14 Bridgegate Business Park

Gatehouse Way

Aylesbury

Buckinghamshire

HP19 8XN

United Kingdom

Tel: 44 (0)1296 425665

Fax: 44 (0)1296 425665

[www.rpsupport.co.uk](http://www.rpsupport.co.uk)

### Product Description

DSM Somos® ProtoGen™ 18120 is a liquid, ABS-like, photopolymer that produces accurate parts ideal for general purpose applications. ProtoGen resins are the first stereolithography resins to demonstrate different material properties based on machine exposure control. Based on Somos Oxetane™ chemistry, ProtoGen 18120 offers superior chemical resistance, a wide processing latitude and excellent tolerance to a broad range of temperatures and humidities, both during and after build.

### Applications

This high-temperature resistant, ABS-like photopolymer is used in solid imaging processes, like stereolithography, to build three-dimensional parts. Somos ProtoGen 18120 provides considerable processing latitude and is ideal for the medical, electronic, aerospace and automotive markets that demand accurate RTV patterns, durable concept models, highly accurate and humidity & temperature resistant parts.

### Technical Data: Liquid Properties

Appearance	Translucent
Viscosity	~300 cps @ 30° C
Density	1.16 g/cm <sup>3</sup> @ 25° C

### Technical Data: Optical Properties

E <sub>c</sub>	6.73 mJ/cm <sup>2</sup>	[critical exposure]
D <sub>p</sub>	4.57 mils	[slope of cure-depth vs. ln(E) curve]
E <sub>10</sub>	57.0 mJ/cm <sup>2</sup>	[exposure that gives 0.254 mm (.010 inch) thickness]



ProtoGen™ 18120 is a liquid, ABS-like photopolymer that produces accurate parts ideal for general purpose applications.

### Key Product Benefits:

- Humidity & Temperature Tolerant
- High Dimensional Stability
- Fast Processing Speeds

(continued)

For technical service, please visit: <http://www.dsmsomos.com>

Rev Date: 10/10

**Sales Agent:****RP Support Ltd.**

14 Bridgegate Business Park  
Gatehouse Way  
Aylesbury  
Buckinghamshire  
HP19 8XN  
United Kingdom

Tel: 44 (0)1296 425665  
Fax: 44 (0)1296 425665  
[www.rpsupport.co.uk](http://www.rpsupport.co.uk)

# ProtoGen™ 18120

## Technical Data: Mechanical Properties

ASTM Method		ProtoGen™ 18120 UV Postcure at HOC -2		ProtoGen™ 18120 UV Postcure at HOC +3*		ProtoGen™ 18120 UV & Thermal Postcure	
		Metric	Imperial	Metric	Imperial	Metric	Imperial
D638M	Tensile Strength	51.7 – 54.9 MPa	7.5 – 8.0 ksi	56.9 – 57.1 MPa	8.2 – 8.3 ksi	68.8 – 69.2 MPa	9.9 – 10.0 ksi
D638M	Tensile Modulus	2,620 – 2,740 MPa	381 – 397 ksi	2,540 – 2,620 MPa	370 – 380 ksi	2,910 – 2,990 MPa	422 – 433 ksi
D638M	Elongation at Break	6 – 12%	6 – 12%	8 – 12%	8 – 12%	7 – 8%	7 – 8%
D638M	Poisson's Ratio	0.43 – 0.45	0.43 – 0.45	not recorded	not recorded	0.43	0.43
D790M	Flexural Strength	81.8 – 83.8 MPa	11.9 – 12.2 ksi	83.8 – 86.7 MPa	12.2 – 12.6 ksi	88.5 – 91.5 MPa	13.2 ksi
D790M	Flexural Modulus	2,360 – 2,480 MPa	343 – 359 ksi	2,400 – 2,450 MPa	350 – 355 ksi	2,330 -2,490 MPa	361 ksi
D2240	Hardness (Shore D)	84 - 85	85 – 87	not recorded	not recorded	87 – 88	87 - 88
D256A	Izod Impact-Notched	0.14 – 0.26 J/cm	0.26 – 0.49 ft-lb/in	not recorded	not recorded	0.13 – 0.25 J/cm	0.24 – 0.47 ft-lb/in
D570-98	Water Absorption	0.77%	0.77%	not recorded	not recorded	0.75%	0.75%

## Technical Data: Thermal/Electrical Properties

ASTM Method		ProtoGen™ 18120 UV Postcure at HOC -2		ProtoGen™ 18120 UV & Thermal Postcure	
		Metric	Imperial	Metric	Imperial
E831-05	C.T.E. -40°C - 0°C (-40°F – 32°F)	65.1 – 68.1 µm/m°C	36.2 – 37.8 µin/in°F	63.7 – 71.8 µm/m°C	35.4 – 39.9 µin/in°F
E831-05	C.T.E. 0°C - 50°C (32°F – 122°F)	84.7 – 95.3 µm/m°C	47.1 – 52.9 µin/in°F	75.0 – 107.5 µm/m°C	41.7 – 59.7 µin/in°F
E831-05	C.T.E. 50°C - 100°C (122°F – 212°F)	93.8 – 116.9 µm/m°C	52.1 – 64.9 µin/in°F	99.4 – 111.0 µm/m°C	55.2 – 61.7 µin/in°F
E831-05	C.T.E. 100°C - 150°C (212°F – 302°F)	147.0 – 155.4 µm/m°C	81.7 – 86.3 µin/in°F	143.4 – 173.3 µm/m°C	79.7 – 96.3 µin/in°F
D150-98	Dielectric Constant 60 Hz	3.4 – 3.5	3.4 – 3.5	3.5 – 3.6	3.5 – 3.6
D150-98	Dielectric Constant 1KHz	3.3 – 3.4	3.3 – 3.4	3.4 – 3.5	3.4 – 3.5
D150-98	Dielectric Constant 1MHz	3.1 – 3.2	3.1 – 3.2	3.2 – 3.3	3.2 – 3.3
D149-97a	Dielectric Strength	14.4 – 15.3 kV/mm	365 - 387 V/mil	15.2 – 15.7 kV/mm	386 - 398 V/mil
E1545-00	Tg	71 – 86°C	160 – 187°F	76 – 94°C	169 - 201°F
D648	HDT @ 0.46 MPa (66 psi)	55 – 58°C	132 – 136°F	95 – 97°C	203 - 207°F
D648	HDT @ 1.81 MPa (264 psi)	48 – 50°C	118 – 123°F	79 – 82°C	175 - 180°F

Rev Date: 10/10

[www.dsmsomos.com](http://www.dsmsomos.com)


**DSM Somos®**  
1122 St. Charles Street  
Elgin, Illinois 60120 USA  
Tel: +1-847-697-0400  
Fax: +1-847-468-7785

**DSM Desotech bv**  
3150 AB Hoek van Holland  
The Netherlands  
Tel: +31-1743-15391  
Fax: +31-1743-15530

**DSM Desotech-China**  
476 Li Bing Road  
Zhangjiang Hi-Tech Park,  
Pudong New Area  
Shanghai 201203, China  
Tel: +(86) 21-6141 8064  
Fax: +(86) 21-6141 8088

NOTICE : DSM Somos is an unincorporated subsidiary of DSM Desotech Inc. The information presented herein is based on generally accepted analytical and testing practices and is believed to be accurate. However, DSM Desotech expressly disclaims any product warranties which may be implied including warranty of merchantability and/or fitness for a particular purpose. DSM Desotech's products are sold subject to DSM Desotech's standard terms and conditions of sale, copies of which are available upon request. Purchasers are responsible for determining the suitability of the product for its intended use and the appropriate manner of utilizing the product in purchaser's production processes and applications so as to insure safety, quality and effectiveness. Purchasers are further responsible for obtaining necessary patent rights to practice any invention in connection with the use of purchased product and any other product or process. DSM Desotech reserves the right to change specifications of their products without notice.