

MATERIAL SPECIFICATIONS

PA 605-A

HIGHLIGHTS

- Aluminum filled nylon 12
- Parts exhibit excellent thermal and mechanical properties
- Increased recyclability over other competitive materials
- Metallic grey surface finish

APPLICATIONS

- Wind tunnel models and components
- Automotive under hood mechanisms
- Rapid tooling and fixtures
- Ideal for applications requiring stiffness and thermal conductivity. Finished parts give the appearance of cast aluminum

TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	U.S. STANDARD	METRIC
Colour/Appearance	Visual	Metallic Grey	Metallic Grey
Bulk Density	ASTM D1895	0.387 oz/in ³	0.67 g/cm ³
Average Particle Size (D50)	Laser Diffraction	0.002 inches	55 microns
Particle Size Range (D10-D90)	Laser Diffraction	0.001 - 0.004 inches	35 - 100 microns
Sintered Part Density	ASTM D792	0.85 oz/in ³	1.47 g/cm ³
Heat Detection Temperature	ASTM D648	279°F @ 264 psi	137°C @ 1.82 MPa
Heat Detection Temperature	ASTM D648	356°F @ 66 psi	180°C @ 0.45 MPa
Ultimate Tensile Strength (XY)	ASTM D638	6,236 psi	43 MPa
Ultimate Tensile Strength (Z)	ASTM D638	5,400 psi	37 MPa
Tensile Modulus (XY)	ASTM D638	538,000 psi	3,709 MPa
Flexural Modulus (XY)	ASTM D790	510,000 psi	3,517 MPa
Flexural Strength (XY)	ASTM D790	6,290 psi	44 MPa
Elongation at Break (XY)	ASTM D638	3%	3%
Dielectric Constant	ASTM D150	14.5	14.5
Dielectric Strength	ASTM D149	180 v/mm	180 v/mm

For reference use only. Actual properties may vary significantly from those listed above based on processing parameters, operating conditions and end use applications. The above properties were based on virgin ALM PA 605-A using normal processing parameters on a 2500+ platform as outlined in the ALM Material Processing Guide. Advanced Laser Materials, LLC makes no warranties of materials for any application, nor does it make a warranty of any type, expressed or implied, but not limited to, the warranties of merchantability for a particular purpose.



RP Support Ltd.
14 Bridgegate Business Park
Gatehouse Way
Aylesbury
Buckinghamshire
HP19 8XN
United Kingdom

☎ +44 (0)1296 425665
✉ +44 (0)1296 425665
✉ support@rpsupport.co.uk



ALM PA 605-A: 02.20.2013