



Somos® EvoLve 128

A durable stereolithography material that creates parts ready for functional testing

Product Description

Somos® EvoLve 128 is a durable stereolithography material that produces accurate, high-detailed parts and has been designed for easy finishing. It has a look and feel that is almost indistinguishable from finished traditional thermoplastics, making it perfect for building parts and prototypes for functional testing applications – resulting in time, money and material savings during product development.

Somos® EvoLve 128 is an outstanding material for industries such as aerospace, automotive, medical, consumer products and electronics.

Key Benefits

- Easy to clean & finish
- High strength & durability
- Accurate & dimensionally stable
- High detail

Ideal Applications

- Tough, functional prototypes
- Snap-fit designs
- Jigs & fixtures

Somos® EvoLve 128 Technical Data

Liquid Properties		Optical Properties		
Appearance	White	E_c	9.3 mJ/cm ²	[critical exposure]
Viscosity	~380 cps @ 30°C	D_p	4.3 mils	[slope of cure-depth vs. ln (E) curve]
Density	~1.12 g/cm ³ @ 25°C	E_{10}	95.1 mJ/cm ²	[exposure that gives 0.254 mm (.010 inch) thickness]

Mechanical Properties		UV Postcure	
ASTM Method	Property Description	Metric	Imperial
D638M	Tensile Modulus	2,964 MPa	430 ksi
D638M	Tensile Strength at Yield	56.8 MPa	8.2 ksi
D638M	Elongation at Break	11%	
D2240	Flexural Modulus	2,654 MPa	385 ksi
D256A	Izod Impact (Notched)	38.9 J/m	0.729 ft-lb/in
D2240	Hardness (Shore D)	82	
D570-98	Water Absorption	0.40%	

Thermal/Electrical Properties		UV Postcure	
ASTM Method	Property Description	Metric	Imperial
E831-05	C.T.E. -40 - 0°C (-40 - 32°F)	56.5 $\mu\text{m}/\text{m}^\circ\text{C}$	31.4 $\mu\text{in}/\text{in}^\circ\text{F}$
E831-05	C.T.E. 0 - 50°C (32 - 122°F)	76.5 $\mu\text{m}/\text{m}^\circ\text{C}$	42.5 $\mu\text{in}/\text{in}^\circ\text{F}$
E831-05	C.T.E. 50 - 100°C (122 - 212°F)	163 $\mu\text{m}/\text{m}^\circ\text{C}$	90.8 $\mu\text{in}/\text{in}^\circ\text{F}$
E831-05	C.T.E. 100 - 150°C (212 - 302°F)	174 $\mu\text{m}/\text{m}^\circ\text{C}$	96.5 $\mu\text{in}/\text{in}^\circ\text{F}$
D150-98	Dielectric Constant 60 Hz	3.9	
D150-98	Dielectric Constant 1 KHz	3.7	
D150-98	Dielectric Constant 1 MHz	3.5	
D149-97a	Dielectric Strength	31 kV/mm	788 V/mil
D648	HDT @ 0.46 MPa (66 psi)	52.3°C	126°F
D648	HDT @ 1.81 MPa (264 psi)	49.6°C	121°F

These values may vary and depend on individual machine processing and post-curing practices.

DSM Functional Materials Somos® Material Group

North America

1122 St. Charles Street
Elgin, Illinois 60120
USA
Phone: +1.847.697.0400

Europe

Slachthuisweg 30
3151 XN Hoek van Holland
The Netherlands
Phone: +31.174.315.391

China

476 Li Bing Road
Zhangjiang Hi-Tech Park
Pudong New Area
Shanghai 201203, China
Phone: +86.21.6141.8064

NOTICE: Somos® is a registered trademark of Royal DSM N.V. Somos® is an unincorporated subsidiary of DSM Desotech Inc. The information presented herein is based on generally accepted analytical and testing practices and is believed to be accurate. However, DSM Desotech expressly disclaims any product warranties which may be implied including warranties of merchantability and/or fitness for a particular purpose. DSM Desotech's products are sold subject to DSM Desotech's standard terms and conditions of sale, copies of which are available upon request. Purchasers are responsible for determining the suitability of the product for its intended use and the appropriate manner of utilizing the product in purchaser's production processes and applications so as to insure safety, quality and effectiveness. Purchasers are further responsible for obtaining necessary patent rights to practice any invention in connection with the use of purchased product and any other product or process. DSM Desotech reserves the right to change specifications of their products without notice. © 2016 DSM IP ASSESTS B.V. All rights reserved.

Visit us online at www.dsm.com/somos

032016 | SOMOS-EVOLVE 128-SS-PDSA4



About RPS

RPS has been in operation over ten years and our engineers collectively have decades of experience working with stereolithography and laser sintering equipment. With proven experience in 3D printing, engineering, electronics, computer-aided engineering and more, we understand the technology and can offer advice on how it can suit your specific application.

We manufacture the **NEO800** stereolithography system, designed, developed and built by RPS engineers. We are also an HP Channel Partner of HP's Multi-Jet Fusion technology and offer a range of materials and software through our partnership with market-leading suppliers ALM, DSM Somos® and Materialise.

    +44 (0) 1296 425665 | support@rps.ltd | www.rps.ltd

14 Bridgegate Business Park | Gatehouse Way | Aylesbury | Buckinghamshire | HP19 8XN | UK