



## Somos® NeXt

An extremely durable stereolithography material that creates parts ready for functional testing

### Product Description

Through continuous innovation and collaboration with our customers over many years, Somos® delivers the next generation in toughness and durability with Somos® NeXt.

Somos® NeXt is a highly durable stereolithography material which produces very accurate parts with high feature resolution. This material is ideal for the production of tough, complex parts that also exhibit excellent moisture and thermal resistance. Somos® NeXt has a look and feel that is almost indistinguishable from finished traditional thermoplastics, making it perfect for building parts and prototypes for functional testing applications — resulting in time, money and material savings during product development.

Somos® NeXt is an outstanding material for industries such as aerospace, automotive, medical, consumer products and electronics.

### Key Benefits

- Superior strength and durability
- Exceptionally versatile
- Thermoplastic-like performance, look and feel

### Ideal Applications

- Tough, functional end-use prototypes
- Snap-fit designs
- Jigs and fixtures
- Packaging and sporting goods



#### Seeing was believing for Warrior Sports

During a test game that used professional athletes, hard rubber balls (weighing 5.25 ounces) were caught and thrown using Somos® NeXt prototype lacrosse heads. Speeds of 90+ mph were achieved to test the durability of not only the design of the head, but also, the durability of Somos® NeXt.

Liquid Properties		Optical Properties		
Appearance	White	E <sub>C</sub>	12.0 mJ/cm <sup>2</sup>	[critical exposure]
Viscosity	~1,000 cps @ 30°C	D <sub>P</sub>	5.8 mils	[slope of cure-depth vs. ln (E) curve]
Density	~1.17 g/cm <sup>3</sup> @ 25°C	E <sub>10</sub>	67 mJ/cm <sup>2</sup>	[exposure that gives 0.254 mm (.010 inch) thickness]

Mechanical Properties		UV Postcure	
ASTM Method	Property Description	Metric	Imperial
D638M	Tensile Modulus	2,430 MPa	352 ksi
D638M	Tensile Strength at Yield	42.2 MPa	6.1 ksi
D638M	Tensile Strength at Break	32.8 MPa	4.8 ksi
D638M	Elongation at Break	9%	
D638M	Elongation at Yield	3%	
D638M	Poisson's Ratio	0.43	
D790M	Flexural Strength	69.3 MPa	10.1 ksi
D2240	Flexural Modulus	2,470 MPa	358 ksi
D256A	Izod Impact (Notched)	50 J/m	0.94 ft-lb/in
D2240	Hardness (Shore D)	82	
D570-98	Water Absorption	0.40%	

Thermal/Electrical Properties		UV Postcure	
ASTM Method	Property Description	Metric	Imperial
E831-05	C.T.E. -40 - 0°C (-40 - 32°F)	73 µm/m°C	40.6 µin/in°F
E831-05	C.T.E. 0 - 50°C (32 - 122°F)	111 µm/m°C	61.7 µin/in°F
E831-05	C.T.E. 50 - 100°C (122 - 212°F)	172 µm/m°C	95.6 µin/in°F
E831-05	C.T.E. 100 - 150°C (212 - 302°F)	173 µm/m°C	96.2 µin/in°F
D150-98	Dielectric Constant 60 Hz	4.7	
D150-98	Dielectric Constant 1 KHz	4.0	
D150-98	Dielectric Constant 1 MHz	3.6	
D149-97a	Dielectric Strength	15.2 kV/mm	386 V/mil
D648	HDT @ 0.46 MPa (66 psi)	56°C	133°F
D648	HDT @ 1.81 MPa (264 psi)	50°C	122°F

These values may vary and depend on individual machine processing and post-curing practices.

## DSM Functional Materials Somos® Material Group

### North America

1122 St. Charles Street  
Elgin, Illinois 60120  
USA  
Phone: +1.847.697.0400

### Europe

Slachthuisweg 30  
3151 XN Hoek van Holland  
The Netherlands  
Phone: +31.174.315.391

### China

476 Li Bing Road  
Zhangjiang Hi-Tech Park  
Pudong New Area  
Shanghai 201203, China  
Phone: +86.21.6141.8064

NOTICE : Somos® is a registered trademark of Royal DSM N.V. Somos® is an unincorporated subsidiary of DSM Desotech Inc. The information presented herein is based on generally accepted analytical and testing practices and is believed to be accurate. However, DSM Desotech expressly disclaims any product warranties which may be implied including warranties of merchantability and/or fitness for a particular purpose. DSM Desotech's products are sold subject to DSM Desotech's standard terms and conditions of sale, copies of which are available upon request. Purchasers are responsible for determining the suitability of the product for its intended use and the appropriate manner of utilizing the product in purchaser's production processes and applications so as to insure safety, quality and effectiveness. Purchasers are further responsible for obtaining necessary patent rights to practice any invention in connection with the use of purchased product and any other product or process. DSM Desotech reserves the right to change specifications of their products without notice. © 2015 DSM IP ASSESTS B.V. All rights reserved.

052015 | SOMOS-NEXT-SS-PDS44

Visit us online at [www.dsm.com/somos](http://www.dsm.com/somos)



## About RPS

RPS has been in operation over ten years and our engineers collectively have decades of experience working with stereolithography and laser sintering equipment. With proven experience in 3D printing, engineering, electronics, computer-aided engineering and more, we understand the technology and can offer advice on how it can suit your specific application.

We manufacture the **NEO800** stereolithography system, designed, developed and built by RPS engineers. We are also an HP Channel Partner of HP's Multi-Jet Fusion technology and offer a range of materials and software through our partnership with market-leading suppliers ALM, DSM Somos® and Materialise.

    +44 (0) 1296 425665 | [support@rps.ltd](mailto:support@rps.ltd) | [www.rps.ltd](http://www.rps.ltd)

14 Bridgegate Business Park | Gatehouse Way | Aylesbury | Buckinghamshire | HP19 8XN | UK