



Somos® WaterShed XC 11122

An easy to use, low viscosity, water-resistant stereolithography material for use in numerous applications

Product Description

As one of the industry's most popular materials, Somos® WaterShed XC 11122 is the clear solution for numerous applications. Whether you're a designer looking for highly detailed parts with superior clarity and water resistance, or an engineer focusing on durability for functional testing, Somos® WaterShed XC 11122 mimicks the look and feel of clear thermoplastics, such as ABS and PBT.

Somos® WaterShed XC 11122 produces optically clear parts with a smooth finish and it's ease of use helps to shorten product development and testing. This versatility means Somos® WaterShed XC 11122 is the ideal material in markets such as automotive, aerospace and consumer electronics for applications including packaging, RTV patterns, durable concept models, wind tunnel testing and investment casting patterns.

Key Benefits

- Easy to use and finish
- Superior moisture resistance
- Exceptional clarity

Ideal Applications

- Consumer products
- Fluid flow analysis
- Duct work
- Investment casting
- Lenses

Somos® WaterShed XC 1122 Technical Data

Liquid Properties		Optical Properties		
Appearance	Optically clear, near colorless	E _C	11.5 mJ/cm ²	[critical exposure]
Viscosity	~260 cps @ 30°C	D _P	6.50 mils	[slope of cure-depth vs. ln (E) curve]
Density	~1.12 g/cm ³ @ 25°C	E ₁₀	54 mJ/cm ²	[exposure that gives 0.254 mm (.010 inch) thickness]
		D542	1.514	Index of Refraction (cured)

Mechanical Properties		UV Postcure	
ASTM Method	Property Description	Metric	Imperial
D638M	Tensile Strength at Break	50.4 MPa	7.3 ksi
D638M	Elongation at Break	15.5%	
D638M	Elongation at Yield	3%	
D638M	Tensile Modulus	2,770 MPa	402 ksi
D790M	Flexural Strength	68.7 MPa	10.0 ksi
D2240	Flexural Modulus	2,205 MPa	320 ksi
D256A	Izod Impact (Notched)	25 J/m	0.47 ft-lb/in
D570-98	Water Absorption	0.35%	

Thermal/Electrical Properties		UV Postcure	
ASTM Method	Property Description	Metric	Imperial
E831-05	C.T.E. -40 - 0°C (-40 - 32°F)	67 µm/m°C	37 µin/in°F
E831-05	C.T.E. 0 - 50°C (32 - 122°F)	93 µm/m°C	52 µin/in°F
E831-05	C.T.E. 50 - 100°C (122 - 212°F)	180 µm/m°C	100 µin/in°F
E831-05	C.T.E. 100 - 150°C (212 - 302°F)	187 µm/m°C	104 µin/in°F
D150-98	Dielectric Constant 60 Hz	4.0	
D150-98	Dielectric Constant 1 KHz	3.8	
D150-98	Dielectric Constant 1 MHz	3.5	
D149-97a	Dielectric Strength	15.9 kV/mm	404 V/mil
E1545-00	T _g	43°C	109°F
D648	HDT @ 0.46 MPa (66 psi)	50°C	122°F
D648	HDT @ 1.81 MPa (264 psi)	49°C	120°F

These values may vary and depend on individual machine processing and post-curing practices.

DSM Functional Materials Somos® Material Group

North America

1122 St. Charles Street
Elgin, Illinois 60120
USA
Phone: +1.847.697.0400

Europe

Slachthuisweg 30
3151 XN Hoek van Holland
The Netherlands
Phone: +31.174.315.391

China

476 Li Bing Road
Zhangjiang Hi-Tech Park
Pudong New Area
Shanghai 201203, China
Phone: +86.21.6141.8064

Visit us online at www.dsm.com/somos

NOTICE : Somos® is a registered trademark of Royal DSM N.V. Somos® is an unincorporated subsidiary of DSM Desotech Inc. The information presented herein is based on generally accepted analytical and testing practices and is believed to be accurate. However, DSM Desotech expressly disclaims any product warranties which may be implied including warranties or merchantability and/or fitness for a particular purpose. DSM Desotech's products are sold subject to DSM Desotech's standard terms and conditions of sale, copies of which are available upon request. Purchasers are responsible for determining the suitability of the product for its intended use and the appropriate manner of utilizing the product in purchaser's production processes and applications so as to insure safety, quality and effectiveness. Purchasers are further responsible for obtaining necessary patent rights to practice any invention in connection with the use of purchased product and any other product or process. DSM Desotech reserves the right to change specifications of their products without notice. © 2015 DSM IP ASSESTS B.V. All rights reserved.

052015 | SOMOS-WATERSHED-SS-PDSA4



About RPS

RPS has been in operation over ten years and our engineers collectively have decades of experience working with stereolithography and laser sintering equipment. With proven experience in 3D printing, engineering, electronics, computer-aided engineering and more, we understand the technology and can offer advice on how it can suit your specific application.

We manufacture the **NEO800** stereolithography system, designed, developed and built by RPS engineers. We are also an HP Channel Partner of HP's Multi-Jet Fusion technology and offer a range of materials and software through our partnership with market-leading suppliers ALM, DSM Somos® and Materialise.

    +44 (0) 1296 425665 | support@rps.ltd | www.rps.ltd

14 Bridgegate Business Park | Gatehouse Way | Aylesbury | Buckinghamshire | HP19 8XN | UK